TECHNICAL DATA SHEET

SAFETY & SECURITY WINDOW FILM

DYED SAFETY · 8 MIL

SAFETY 8 35

38% VISIBLE LIGHT	**37%** SOLAR ENERGY REJECTED
265 lb/in BREAK STRENGTH	**99%** UV REJECTED



PERFORMANCE DATA

Visible light transmitted (VLT)	**38%**
Visible light reflectance	**6%**
Total solar energy rejected	**37%**
Solar transmitted / absorbed / reflected	**52 / 41 / 7%**
UV rejected	**99%**
Winter median U-value	**1.04**
Film type	**Dyed, non-reflective**

PHYSICAL PROPERTIES

Film thickness	**8 mil (0.008 in)**
Tensile strength	**30,400 psi**
Break strength	**265 lb/in**
Elongation at break	**>100%**
Peel strength	**2,750 g/in**
Puncture strength	**173 lb**

BENEFITS

- **Privacy with a clear view**
  A medium shade that balances privacy and visibility.
- **Holds broken glass in place**
  Keeps shards together to help protect people from flying glass.
- **Solar heat control**
  Rejects 37% of total solar energy for more comfortable rooms.
- **UV protection**
  Blocks 99% of UV rays to help protect furnishings from fading.
- **Non-reflective look**
  Only 6% visible reflectance: no mirror effect.

SHADES · 8 MIL

05	20	**35**	50	70

All tested materials were applied on a ¼″ clear glass surface in accordance with industry standard tests. Data is for comparison purposes only.

DC INTERNATIONAL
7868 NW 62nd Street, Miami, FL 33166
305-431-6570 · WhatsApp
www.dcifilms.com