TECHNICAL DATA SHEET

SAFETY & SECURITY WINDOW FILM

SAFETY & SECURITY LINE

SAFETY 12 MIL



87% VISIBLE LIGHT	**12 mil** FILM THICKNESS
330 lb/in BREAK STRENGTH	**ANSI Z97.1** TESTED / RATED TO

PERFORMANCE DATA

Visible light transmitted (VLT)	**87%**
UV rejected	**99%**
Total solar energy rejected	**19%**
Glare reduction	**1%**
Solar reflected / absorbed / transmitted	**9 / 13 / 78%**
Visible reflectance int. / ext.	**8 / 8%**
Shading coefficient / SHGC	**0.93 / 0.81**
Tested / rated to	**ANSI Z97.1**

PHYSICAL PROPERTIES

Tensile strength (avg.)	**32,000 psi**
Break strength	**330 lb/in**
Puncture strength	**>215 lb**
Elongation	**>200%**
Peel strength (adhesion)	**>5 lb/in**
Tone / product code	**Clear / FSAF1260100**

BENEFITS

- **Commercial protection**
  Storefronts and schools; rated to ANSI Z97.1.
- **Holds broken glass in place**
  Keeps shards together to help protect people from flying glass.
- **Delays forced entry**
  Adds time and effort for anyone trying to get through the glass.
- **Optically clear with UV protection**
  87% visible light and 99% UV rejection: the view stays the same.

THICKNESSES (MIL)

4 | 7 | 8 | 11 | **12** | 14 | 16 | 18 | 21 | 24

All tested materials were applied on a ¼″ clear glass surface in accordance with industry standard tests. Data is for comparison purposes only. Also available as an exterior film.

DC INTERNATIONAL
7868 NW 62nd Street, Miami, FL 33166
305-431-6570 · WhatsApp
www.dcifilms.com